

Caratteristiche Characteristics	Metodo di prova Test Method	Unità Unit	Valore Value
Composizione / Composition	ISO 1833 o ISO 5088	%	1% PU- 78% PVC – 9% COTT- 12% PES
Peso totale/ Total weight	ISO 3801 –EN29073/1	g/m²	760 ± 5 %
Larghezza / Usable width	ISO 3932	cm	140 ± 5%
Spessore/ Thickness	UNI 9947	mm	1,10 ± 10%
 Resistenza alla luce/ Light resistance	UNI EN ISO 12947-2:2000	Scala dei blu Bluescale	>5
 Antibacterial-Antimibrobial Efficacy Against Bacteria MRSA	ISO 22196:2011 A.A.T.C.C. Test Method 30-2004	%	Inhibition > 99%
Solidità del colore allo sfregamento a secco e umido Colour fastness to dry and wet rubbing	BS EN ISO 105 X12	Scala dei grigi Greyscale	5
 Resistenza all'abrasione Abrasion resistance	UNI EN ISO 12947-2:2000 <i>Martindale Test</i>	Cicli Cycles	>100.000



Resistenza al fuoco
Fire resistance

IMO FTP CODE

BS 5852-1:1979
Match and Cigarette

UNI 9175:2010
Classe 1.IM

EN 1021-2:2006

CALIFORNIA T.B. 117-13

DIN 4102-1

NFPA 260

FMVSS 302

